

## 1. Preface

The purpose of this product specification is to provide technical information for the rechargeable Lithium-ion cylindrical battery ULR17335, manufactured and supplied by Unique Energy.

## 2. Description and Model

2.1 Description	Rechargeable Lithium-ion cylindrical battery
2.2 Model	ULR17335

## 3. Specification

3.1 Capacity	Nominal	700mAh
	Typical	720mAh
3.2 Charging Voltage		4.20V
3.3 Nominal Voltage		3.7V at 0.2C mA
3.4 Standard Charging Method		Constant current:350mA Constant voltage 4.20V
3.5 Cut-off Discharge Voltage		3.00V
3.6 Max.Discharge Current		1050mA
3.7 Max.Charge Current		700mA
3.8 Cycle Life		>500 cycles at 0.5C mA discharge
3.9 Ambient Temperature		
	for Standard Charge	0°C~ 45°C
	for Discharge	-20°C~ 60°C
3.10 Storage		
	for within the temperature	-20°C~ 60°C
	for within the humidity	≤75%
3.11 Energy Density		
	Wh/L	~320
	Wh/Kg	~150
3.12 Weight of Bare Cell		~26g
3.13 Charge State Internal Impedance		<80m Ω

## 4. Appearance

Appearance shall be free from any remarkable scratch,flaws, rust, discoloration or electrolyte leakage(visible or by smell)

## 5. Standard Test condition

### 5.1 Environment Conditions

Unless otherwise specified,all test stated in this Product Specification are conducted within the temperature 15~25°C and the humidity 45~85%RH.

## 5.2 Test Equipment


### (1) Impedance meter

The impedance meter with AC 1kHz should be used


## 6. Test Procedure and Its Standard

Item	Measuring Procedure	Standard
6.1 Appearance	Visual	No Defect and Leak
6.2 Dimension	Caliper	As item 8
6.3 Weight	Scale	As item 3.12
6.4 Maximum Charge Current	CCCV (Constant Current Constant Voltage)	700mA
6.5 Full charge	CCCV	CC-0.5CmA CV- 4.2V End-Current 7mA
6.6 Open Circuit Voltage	Within 1hr after full charge,measure Open circuit voltage	>4.10V
6.7 Internal Impedance	Measure the battery with 1kHz AC	<80m $\Omega$
6.8 Discharge Capacity	Within 1hr after full charge,discharge until final discharge,at 0.2C mA and measure the capacity	>700mAh
6.9 Maximum Discharge Current	Until final discharge voltage	1050 mA
6.10 Charge/Discharge Cycle Life	Charge:CCCV,CC- 0.5CmA,CV- 4.2V End-Current 7mA  Discharge:0.5CmA to 3.00V,This charge/discharge shall be repeated 500 times	Discharge capacity  should be >70% of item 6.8
6.11 Leakage Proof	After full charging,the battery shall be stored at 40 $\pm$ 2 $^{\circ}$ C and humidity 80 $\pm$ 5%for 21 days	No leakage should be observed by visual inspection
6.12 Temperature Characteristics	1)After full charge at 20 $\pm$ 5 $^{\circ}$ C ,stand at -20 $\pm$ 2 $^{\circ}$ C for 18h,then discharge at 0.2C mA and measure the capacity 2)After full charge at 20 $\pm$ 5 $^{\circ}$ C ,stand at 55 $\pm$ 2 $^{\circ}$ C for 2hrs ,then discharge at 1C mA and measure the capacity	Discharge capacity should be>60% of item 6.8 and no abnormality on its appearance and stucture
6.13 Charge Retension	After full charging,stand at 20 $\pm$ 5 $^{\circ}$ C for 28 days,measure the discharge capacity according to item 6.8	Discharge capacity should be>85% of item 6.8


**7.1 Charge/Discharge Characteristics**  
 Charge:CC/CV 4.2V, 350mA(0.5C),  
 End- current 7mA  
 Discharge:350mA(0.5C) Cut-off at 3.00V  
 Temperature:25°C



**7.3 Temperature Characteristics**  
 Charge: CC/CV 4.2V 0.5CA,End-Current 7mA  
 Discharge:As item 6.10



**7.2 Charge/Discharge Cycle Life**  
 Charge:CC/CV 4.2V, 0.5CmA,  
 End-Current 7mA  
 Discharge:0.5CmA,Cut-off at 3.00V  
 Temperature:25°C



**8. Dimension(Bare cell) mm**

